

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 05-017538

(43)Date of publication of application : 26.01.1993

(51)Int.Cl.

G08F220/24
G08F 2/24
G08F222/02

(21)Application number : 03-264266

(71)Applicant : HOECHST GOSEI KK

(22)Date of filing : 11.07.1991

(72)Inventor : SHIMOKAWA WATARU
FUKAZAWA YUJI

(54) METHOD FOR PRODUCING FLUORINE-CONTAINING ACRYL COPOLYMER AQUEOUS EMULSION AND COMPOSITION THEREFOR

(57)Abstract:

PURPOSE: To produce the subject emulsion having excellent water-repellency, oil repellency and stability by emulsifying a perfluoroalkyl acrylate monomer and an α,β -ethylenic unsaturated monomer and subsequently radically copolymerizing the mixture. CONSTITUTION: (A) 2-40mol.% of a 6-12C alkyl group-having perfluoroalkyl acrylate monomer, (B) 0.1-15mol.% of a carboxyl group-containing α,β -ethylenic unsaturated monomer copolymerizable with the component A, (C) 0-25mol.% of a hydroxyl group-containing α,β -ethylenic unsaturated monomer copolymerizable with the components A and B, and (D) some other α,β -ethylenic unsaturated monomer copolymerizable with the components A, B and C are emulsified in water in the presence of a surfactant. The emulsion is preferably subjected to an ultrasonic wave-radiating treatment or to a high pressure homogenizing treatment to minimize the emulsion particles into diameters of $\leq 0.3\mu$ (preferably 0.3-0.05 μ), followed by radically polymerizing the particles to provide the objective emulsion.

LEGAL STATUS

[Date of request for examination] 21.06.1993

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 2137572

[Date of registration] 31.07.1998

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

(19)日本国特許庁(JP)

(12) 公開特許公報(A)

(11)特許出願公開番号

特開平5-17538

(43)公開日 平成5年(1993)1月26日

| (51)Int.Cl. ⁵ | 識別記号 | 庁内整理番号 | F I | 技術表示箇所 |
|--------------------------|------|----------|-----|--------|
| C 0 8 F 220/24 | MMT | 7242-4 J | | |
| 2/24 | MBP | 7442-4 J | | |
| 222/02 | MLU | 7242-4 J | | |

審査請求 未請求 請求項の数7(全 8 頁)

(21)出願番号 特願平3-264266

(22)出願日 平成3年(1991)7月11日

(71)出願人 000113148

ヘキスト合成株式会社

東京都港区赤坂4丁目10番33号

(72)発明者 下川 渉

静岡県小笠郡大東町千浜3330番地 ヘキスト合成株式会社静岡研究所内

(72)発明者 深沢 裕二

静岡県小笠郡大東町千浜3330番地 ヘキスト合成株式会社静岡研究所内

(74)代理人 弁理士 渡辺 秀夫

(54)【発明の名称】 含フッ素アクリル系共重合体水性エマルジョンの製造方法及びその組成物

(57)【要約】

【目的】 ▲撥▼水性と▲撥▼油性及び安定性に優れた、微粒子状の含フッ素アクリル共重合体水性エマルジョンの製造方法と、得られたエマルジョンおよび他の物質との混合物を提供する。

【構成】 炭素数6～12のアルキル基を有するパーフルオロアルキルアクリレートと、共重合可能なカルボキシル基含有 α 、 β -エチレン性不飽和単量体と、共重合可能なヒドロキシル基含有 α 、 β -エチレン性不飽和単量体と、その他の共重合可能な α 、 β -エチレン性不飽和単量体を、界面活性剤を用いて水中に乳化分散させ、粒径を0.3 μ m以下の粒子としてから重合してエマルジョンを製造する。得られたエマルジョンはそのまま使用するほか他の物質と混合して使用する。